

NATUCORK

PROJECTED CORK

Description

NATUCORK sprayed cork is a flexible mortar that uses natural cork, making it an environmentally friendly product. Made from high-quality acrylic resins, it has diverse applications thanks to its ability to thermally and acoustically insulate, be impermeable to rainwater, and adhere firmly to a variety of surfaces.

Properties

- Reduces heat transmission by approximately 20%.
- Great elasticity to resist support contractions.
- Excellent resistance to external climate changes.
- Dampens noise and vibrations, with optimal acoustic absorption and soundproofing.
- Ideal for waterproofing floors, terraces and walkable roofs.
- Wide range of colors for applications on facades and interior decoration.

Technical Data

	NATUCORK
Consumption	1 a 2 m ² /lt per layer
Layer thickness	1,5 mm.
Adhesion Strength	Cement mortar 5.80 Kg/cm ² . Galvanized steel: 5 Kg/cm ² . Glass. 6 Kg/cm ²
Temperature resistance	-20° a 120°
VOC	e/BA 75/40 (2007/2010)máx.:10g/l.
Reaction to fire	M-1, according to UNE 23721:1990

How to use

- 2 coats of NATUCORK are recommended.
- Apply to clean, dry surfaces, free of dust, grease and mold.
- Surfaces containing old paints must be scraped and completely cleaned to ensure adhesion. Apply consolidant if necessary.
- On iron: Remove rust and degrease and apply a coat of anti-corrosion primer.
- Application mode: Spray gun, brush or roller.

Special Precautions

In case of contact with eyes, rinse with plenty of water for 15 minutes. In case of contact with skin, wash with soap and water. Do not eat. If swallowed, do not cause vomiting and seek medical attention immediately. It is recommended to comply with the following measures:

- Good ventilation
- Protective glasses to avoid splashes
- Rubber gloves

Cleaning and Storage

Tools should be cleaned with water immediately after use. Once the material has hardened, it can only be removed by mechanical means.

The product should be stored in its original container, closed and protected from the elements, at temperatures between 10°C and 30°C, in a dry and well-ventilated place, away from heat sources and direct sunlight. The use time is 1 year from the date of manufacture, properly preserved.

www.lunik.cc

Calle Benifaió 38, Guadassuar (Valencia)
CP 46610 Spain
Tel. +34 96 116 38 84